


SURFACE REFINEMENT

FOR BEST RESULTS IN REMOVING SAND SCRATCHES IN THE SHORTEST AMOUNT OF TIME, USE THE FOLLOWING SYSTEM 51 PRODUCTS AND PADS IN THE STEPS OUTLINED BELOW. SAFE FOR USE WITH ROTARY OR DA POLISHERS.

TO ACHIEVE THE BEST RESULTS AND MOST ADVANCED FINISH, SYSTEM 51 SUGGESTS REFINING SAND SCRATCHES AND FINISHING WITH A 1500-2000 GRIT ABRASIVE. FINISHING WITH A FINER GRIT CAN HELP REDUCE COMPOUNDING TIME.

PRODUCTION KIT

STEP 1

PRODUCT	DESCRIPTION	PROCEDURE
 <p>- PRODUCTION CUT, PN 0010-#</p>	<ul style="list-style-type: none"> - HEAVY CUT COMPOUND - REMOVES HEAVY SAND SCRATCHES FROM FRESH OR CURED SURFACES - USE WITH WOOL OR FOAM CUTTING PAD (PN 018WW OR 019F) 	<ul style="list-style-type: none"> - WORK A 4' x 4' AREA AT A TIME - SUGGESTED POLISHER SPEED: 1,400 - 1,800 RPM - USE MEDIUM TO FIRM PRESSURE TO REMOVE STRAIGHT-LINE AND/OR DA SAND SCRATCHES

STEP 2

PRODUCT	DESCRIPTION	PROCEDURE
 <p>- PRO CUT, PN 009-#</p>	<ul style="list-style-type: none"> - MEDIUM CUT COMPOUND - REMOVES MEDIUM TO LIGHT SCRATCHES FROM FRESH OR CURED SURFACES - MINIMIZES SWIRL MARK - USE FOAM POLISHING PAD (PN 027F). CAN ALSO BE USED AS FIRST STEP WITH WOOL PAD (PN 018WW) ON LIGHT SURFACES 	<ul style="list-style-type: none"> - WORK A 4' x 4' AREA AT A TIME - SUGGESTED POLISHER SPEED: 1,400 - 1,800 RPM - USE MODERATE PRESSURE TO REMOVE LIGHT SCRATCHES AND MINIMIZE SWIRL. - KEEP PAD AS FLAT AS POSSIBLE TO SURFACE

STEP 3

PRODUCT	DESCRIPTION	PROCEDURE
 <p>- PERFECT CUT, PN 007-#</p>	<ul style="list-style-type: none"> - FINISHING POLISH - REMOVES SWIRL MARK - LEAVES HIGH-GLOSS FINISH - USE WITH FOAM FINISHING PAD (PN 028F) 	<ul style="list-style-type: none"> - WORK A 4' x 4' AREA AT A TIME - SUGGESTED POLISHER SPEED: 800 - 1,000 RPM - DO NOT BUFF DRY - LEAVE A WET FILM ON THE SURFACE - USE MEDIUM PRESSURE TO REMOVE SWIRL MARKS, USE LIGHT PRESSURE TO POLISH - KEEP PAD AS FLAT AS POSSIBLE TO SURFACE

CLEAN-UP

- WIPE CLEAN WITH A SYSTEM 51 MICRO FIBER TOWEL
- SOAP & WATER WILL CLEAN ANY SLING/EXTRA PRODUCT, EVEN AFTER PRODUCT HAS DRIED.
- WON'T ADHERE TO THE SURFACE OR DISCOLOR TRIM, RUBBER AND/OR PLASTIC

PROTECTION

- SYSTEM 51 SUGGESTS PROTECTING THE FRESHLY POLISHED SURFACE WITH OUR REPLENISH WAX (PN 107-#). A WATERBORNE, CARNAUBA SPRAY WAX
- BODY SHOP SAFE AND FRESH PAINT SAFE - LEAVES 30-45 DAYS PROTECTION AGAINST THE HARSHTEST ELEMENTS!
- SPRAY ON A LIGHT MIST, WIPE AWAY WITH A SYSTEM 51 MICRO FIBER TOWEL, THEN BUFF TO A PERFECT SHINE WITH A SECOND MICRO FIBER TOWEL.

NOTE: MAKE CERTAIN TO NOT CROSS-CONTAMINATE COMPOUNDING/POLISHING PADS WITH OTHER MANUFACTURER'S COMPOUND/PRODUCT. IF A PAD HAS BEEN USED WITH A PRODUCT OTHER THAN SYSTEM 51'S, IT IS SUGGESTED TO NOT USE THAT PAD AND TO START WITH A BRAND NEW, UNUSED PAD. USING PADS THAT ARE NOT STRICTLY DEDICATED TO SYSTEM 51 PRODUCTS MAY RESULT IN AN UNDESIRABLE FINISH. IN ADDITION, CROSS-CONTAMINATING SYSTEM 51 PRODUCTS WITH EACH OTHER MAY ALSO RESULT IN AN UNDESIRABLE FINISH.

CONTACT YOUR SYSTEM 51 REPRESENTATIVE FOR ORDERING INFORMATION

